

VEDAFLEX SIL es una masilla de silicona monocomponente con módulo de elasticidad bajo y de reticulación neutra. Vulcaniza en contacto con la humedad atmosférica, formando un caucho extremadamente flexible y resistente. No es corrosivo y no desprende olores fuertes.

USOS

VEDAFLEX SIL presenta una excelente adherencia en la mayoría de soportes de uso habitual en construcción: vidrio, hormigón, aluminio, PVC, etc.

Recomendado principalmente para :

- Impermeabilización de juntas entre el hormigón y la carpintería estructural
- Sellado de juntas alrededor de la carpintería de madera, metal y PVC
- Juntas de prefabricación pesada y ligera
- Juntas de estanqueidad para muros cortina
- Cualquier aplicación que precise una masilla inodoro
- Juntas de estanqueidad en la industria (frío, climatización, salas blancas,...)



PROPIEDADES TÉCNICAS

Propiedades físicas antes de la reticulación		
Aspecto	Pasta tixotrópica	
Densidad	1,25	
Formación de piel	4 - 7 min.	
Temperatura de aplicación	+ 5°C a + 40°C	
Propiedades físicas después de la reticulación		
Temperatura de servicio	- 40 °C a + 150°C	
Propiedades mecánicas		
Dureza Shore A	DIN 53505	25
Módulo 100 %	ISO 8339	0,40 MPa
Resistencia a la rotura	ISO 8339	1,40 MPa
Alargamiento de rotura	ISO 8339	550 %

ENVASES Y ALMACENAMIENTO

VEDAFLEX SIL se suministra en cajas de 24 cartuchos de 300 ml. Siempre que se conserve en el envase original cerrado, en un lugar fresco y seco, puede almacenarse 12 meses una temperatura de entre 5°C y 25°C.

COLORES

Blanco, gris, castaño, negro, bronce, marfil.

INSTALACIÓN

Los soportes deben estar limpios, secos, libres de polvo, grasa u otros productos que impidan la correcta adherencia de la silicona. Para la limpieza de los soportes deben utilizarse productos adecuados, siguiendo siempre las recomendaciones del proveedor de los soportes. En caso de soportes no habituales, se recomienda hacer previamente una prueba para determinar la necesidad de utilizar imprimación. Las juntas de VEDAFLEX SIL no se pueden pintar.

DECLARATION OF PERFORMANCE

According Annex III of the regulation (EU) N° 305/2011

Vedaflexsil-20140408

1. Unique identification code of the product-type:

Vedaflexsil

2. Type, batch or serial number or any other element allowing identification of the construction product as required pursuant to Article 11(4):

Vedaflexsil, batch number: see packaging of the product

3. Intended use/es:

Sealant for façade for interior and exterior application (intended for use in cold climates) EN 15651-1:2012 F-EXT-INT-CC 25LM

Sealant used for sealing glazing applications (intended for use in cold climates) EN 15651-2 G-CC 25LM

4. Name, registered trade name or registered trade mark and contact address of the manufacturer as required pursuant to Article 11(5)

GV2 VEDA FRANCE
20 Allée de érables, Bat E
FR-93420 Villepinte

5. Where applicable, name and contact address of the authorised representative whose mandate covers the tasks specified in Article 12(2)

Not relevant

6. System or systems of assessment and verification of constancy of performance of the construction product as set out in Annex V:

System 3 for the type testing and System 3 for the reaction to fire

7. In case of the declaration of performance concerning a construction product covered by a harmonised standard:

The notified body SKZ - TeConA GmbH, D-97076 Würzburg, Friedrich-Bergius-Ring 22, identification number 1213, performed the type testing under system 3 according to EN 15651 part 1 and 2 and issued a test report.

The notified body SKZ - TeConA GmbH, D-97076 Würzburg, Friedrich-Bergius-Ring 22, identification number 1213, performed the testing of the reaction to fire under system 3 according to EN 15651 and issued a test report.

8. In case of the declaration of performance concerning a construction product for which a European Technical Assessment has been issued:

Not relevant

9. Declared performance/s

EN 15651-1 F-EXT-INT-CC 25LM

Conditioning: Method A

Substrate: Aluminium w/o Primer

Essential Characteristics	Performance	Harmonised technical specification
REACTION TO FIRE (EN 13501)	Class E	EN 15651-1: 2012
RELEASE OF CHEMICALS DANGEROUS TO THE ENVIRONMENT AND HEALTH	NPD	EN 15651-1: 2012
WATER TIGHTNESS AND AIR TIGHTNESS		
Resistance to flow (EN ISO 7390)	$\leq 3\text{mm}$	EN 15651-1: 2012
Loss of volume (EN ISO 10563)	$\leq 10\%$	EN 15651-1: 2012
Tensile properties (i.e. at maintained extension after immersion in water at 23°C) (EN ISO 10590)	NF	EN 15651-1: 2012
Tensile properties (i.e. secant modulus) for non-structural low modulus sealants used in joints in cold climate areas (-30°C) (EN ISO 8339)	$\leq 0,9 \text{ N/mm}^2$	EN 15651-1: 2012
Tensile properties (i.e. at maintained extension) for non-structural low modulus sealants used in joints in cold climate areas (-30°C) (EN ISO 8340)	NF	EN 15651-1: 2012
DURABILITY (EN ISO 8340, EN ISO 9047, EN ISO 10590)	Pass	EN 15651-1: 2012

EN 15651-2 G-CC 25LM

Conditioning: Method A

Substrate: Aluminium w/o Primer

Essential Characteristics	Performance	Harmonised technical specification
REACTION TO FIRE (EN 13501)	Class E	EN 15651-2: 2012
RELEASE OF CHEMICALS DANGEROUS TO THE ENVIRONMENT AND HEALTH	NPD	EN 15651-2: 2012
WATER TIGHTNESS AND AIR TIGHTNESS		
Resistance to flow (EN ISO 7390)	≤ 3mm	EN 15651-2: 2012
Loss of volume (EN ISO 10563)	≤ 10%	EN 15651-2: 2012
Adhesion/cohesion properties after exposure to heat, water and artificial light (EN ISO 11431)	NF	EN 15651-2: 2012
Elastic recovery (EN ISO 7389)	≥ 60 %	EN 15651-2: 2012
Tensile properties (i.e. secant modulus) for non-structural low modulus sealants used in joints in cold climate areas (-30°C) (EN ISO 8339)	≤ 0,9 N/mm ²	EN 15651-2: 2012
Tensile properties (i.e. at maintained extension) for non-structural low modulus sealants used in joints in cold climate areas (-30°C) (EN ISO 8340)	NF	EN 15651-2: 2012
DURABILITY (EN ISO 8340, EN ISO 9047, EN ISO 10590)	Pass	EN 15651-2: 2012

NF = no failure according to ISO 11600

NPD = No performance declared

10. The performance of the product identified in points 1 and 2 is in conformity with the declared performance in point 9.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 4.

Signed for and on behalf of the manufacturer by:

Villepinte, 22.05.2025

L. Randé, Technical Director

Annex:

According to Art. 6 (5) of the Regulation (EU) No. 305/2011 a Safety Data sheet according Regulation (EU) No. 1907/2006 (REACH), Annex II is available on the website to support this Declaration of Performance

DECLARATION OF PERFORMANCE

According Annex III of the regulation (EU) N° 305/2011 as it has effect in the United Kingdom in respect of Great Britain.

Vedaflexsil-20140408

1. Unique identification code of the product-type:

Vedaflexsil

2. Type, batch or serial number or any other element allowing identification of the construction product as required pursuant to Article 11(4):

Vedaflexsil, batch number: see packaging of the product

3. Intended use/es:

Sealant for façade for interior and exterior application (intended for use in cold climates) EN 15651-1:2012 F-EXT-INT-CC 25LM

Sealant used for sealing glazing applications (intended for use in cold climates) EN 15651-2 G-CC 25LM

4. Name, registered trade name or registered trade mark and contact address of the manufacturer as required pursuant to Article 11(5)

GV2 VEDA FRANCE
20 Allée de érables, Bat E
FR-93420 Villepinte

5. Where applicable, name and contact address of the authorised representative whose mandate covers the tasks specified in Article 12(2)

Not relevant

6. System or systems of assessment and verification of constancy of performance of the construction product as set out in Annex V:

System 3 for the type testing and System 3 for the reaction to fire

7. In case of the declaration of performance concerning a construction product covered by a harmonised standard:

The notified body 4ward Testing Ltd, 5 Hampers Common Industrial Estate, Petworth, West Sussex GU28 9 NR, England, identification number 2538, performed the type testing under system 3 according to EN 15651 part 1, 2 and 3 and issued a test report.

The notified body 4ward Testing Ltd, 5 Hampers Common Industrial Estate, Petworth, West Sussex GU28 9 NR, England identification number 2538, performed the testing of the reaction to fire under system 3 according to EN 15651 and issued a test report.

8. In case of the declaration of performance concerning a construction product for which a European Technical Assessment has been issued:

Not relevant

9. Declared performance/s

EN 15651-1 F-EXT-INT-CC 25LM

Conditioning: Method A

Substrate: Aluminium w/o Primer

Essential Characteristics	Performance	Harmonised technical specification
REACTION TO FIRE (EN 13501)	Class E	EN 15651-1: 2012
RELEASE OF CHEMICALS DANGEROUS TO THE ENVIRONMENT AND HEALTH	NPD	EN 15651-1: 2012
WATER TIGHTNESS AND AIR TIGHTNESS		
Resistance to flow (EN ISO 7390)	≤ 3mm	EN 15651-1: 2012
Loss of volume (EN ISO 10563)	≤ 10%	EN 15651-1: 2012
Tensile properties (i.e. at maintained extension after immersion in water at 23°C) (EN ISO 10590)	NF	EN 15651-1: 2012
Tensile properties (i.e. secant modulus) for non-structural low modulus sealants used in joints in cold climate areas (-30°C) (EN ISO 8339)	NPD	EN 15651-1: 2012
Tensile properties (i.e. at maintained extension) for non-structural low modulus sealants used in joints in cold climate areas (-30°C) (EN ISO 8340)	NPD	EN 15651-1: 2012
DURABILITY (EN ISO 8340, EN ISO 9047, EN ISO 10590)	Pass	EN 15651-1: 2012

EN 15651-2 G-CC 25LM

Conditioning: Method A

Substrate: Aluminium w/o Primer

Essential Characteristics	Performance	Harmonised technical specification
REACTION TO FIRE (EN 13501)	Class E	EN 15651-2: 2012
RELEASE OF CHEMICALS DANGEROUS TO THE ENVIRONMENT AND HEALTH	NPD	EN 15651-2: 2012
WATER TIGHTNESS AND AIR TIGHTNESS		
Resistance to flow (EN ISO 7390)	≤ 3mm	EN 15651-2: 2012
Loss of volume (EN ISO 10563)	≤ 10%	EN 15651-2: 2012
Adhesion/cohesion properties after exposure to heat, water and artificial light (EN ISO 11431)	NF	EN 15651-2: 2012
Elastic recovery (EN ISO 7389)	≥ 60 %	EN 15651-2: 2012
Tensile properties (i.e. secant modulus) for non-structural low modulus sealants used in joints in cold climate areas (-30°C) (EN ISO 8339)	NPD	EN 15651-2: 2012
Tensile properties (i.e. at maintained extension) for non-structural low modulus sealants used in joints in cold climate areas (-30°C) (EN ISO 8340)	NPD	EN 15651-2: 2012
DURABILITY (EN ISO 8340, EN ISO 9047, EN ISO 10590)	Pass	EN 15651-2: 2012

NF = no failure according to ISO 11600

NPD = No performance declared

10. The performance of the product identified in points 1 and 2 is in conformity with the declared performance in point 9.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 4.

Signed for and on behalf of the manufacturer by:

Villepinte, 22.05.2025

L. Randé, Technical Director

Annex:

According to Art. 6 (5) of the Regulation (EU) No. 305/2011 a Safety Data sheet according Regulation (EU) No. 1907/2006 (REACH), Annex II is available on the website to support this Declaration of Performance.